

THE EFFECT OF TARTARIC ACID IN THE DEPOSITION OF Sb_2S_3 FILMS BY CHEMICAL SPRAY PYROLYSIS

Merike Kriisa¹, Malle Krunks¹, Ilona Oja Acik¹, Erki Kärber¹, and Valdek Mikli²

¹Laboratory of Thin Film Chemical Technologies, Department of Materials Science, Tallinn University of Technology, Tallinn, Ehitajate tee 5, 19086, Estonia

²Chair of Semiconductor Materials Technology, Department of Materials Science, Tallinn University of Technology, Tallinn, Ehitajate tee 5, 19086, Estonia

e-mail: merike.kriisa@ttu.ee

Chemical bath deposited Sb_2S_3 film has been used as absorber in extremely thin absorber solar cells [1]. Here, Sb_2S_3 films were chemically sprayed by atomising aqueous spray solution, consisting of SbCl_3 ($\text{Sb}=2$ mmol/L), thiourea (S) and tartaric acid (TA) in molar ratios of $\text{Sb:S:TA}=1:3:10$ (as utilised in [2,3]) or $1:3:1$, onto preheated glass substrates. The growth temperature (T) varied 205°C - 230°C and 205°C - 355°C for $\text{Sb:S:TA}=1:3:10$ and $1:3:1$, respectively. Effects of TA concentration in spray solution, growth temperature and annealing temperature on the film properties were studied with X-ray diffraction (XRD), scanning electron microscopy (SEM), energy-dispersive X-ray spectroscopy (EDX) and Fourier transform infrared spectroscopy (FTIR). Additionally, thermogravimetric and differential thermal analysis (TG/DTA) of TA was carried out.

Sb_2S_3 film grown at 205°C from solution with $\text{Sb:S:TA}=1:3:10$ is ca. $1 \mu\text{m}$ thick, contains orthorhombic stibnite (Sb_2S_3) phase and high amount of carbon and oxygen residues. Reduced TAs concentration of $1:3:1$ in spray solution leads to orthorhombic Sb_2S_3 film with decreased carbon and oxygen content in the film compared to solutions with $\text{Sb:S:TA}=1:3:10$. Increasing T from 205°C to 355°C decreases the mean crystallite size from 25 nm to 15 nm while a decrease in sulphur and an increase in oxygen content are detected. According to SEM, the morphology and the thickness of Sb_2S_3 film grown from $\text{Sb:S:TA}=1:3:1$ are heterogeneous and film thickness decreases with increasing T. FTIR spectra of Sb_2S_3 film substance confirm that the used T is insufficient for the TA to decompose. According to the TG/DTA, TA decomposition takes place in three steps where 95% of mass is lost by 254°C and TA is totally decomposed at 495°C . Innovatively, Sb_2S_3 films with $E_g=1.7 \text{ eV}$ were sprayed from alcohol solvents.

References

1. S.J. Moon et al., 2010, *J. Phys. Chem. Lett.* 1, 1524
2. S.R. Gadakh and C. H. Bhosale, 2002, *Mater. Chem. Phys.* 78, 367
3. K..Y. Rajpure and C. H. Bhosale 2002, *Mater. Chem. Phys.* 73, 6



Euroopa Liit
Euroopa
Regionaalarengu Fond



Eesti
tuleviku heaks